

NOMENCLATURE

C_A = Concentration of reactant A mol / lit.

Contact Time = volume of catalyst bed / volumetric flow rate

DME = Di Methyl Ether .

E = Activation Energy of the Reaction J / mol .

F = Molar Flow Rate mol . / h .

GHSV = Gas Hourly Space Velocity h⁻¹

GTL = Gas – to – Liquid

ΔH = Enthalpy of Reaction k J / mol .

k = Reaction Rate Constant

k_0 = Frequency or Pre – Exponential Factor

Mpa = Mega Pascal

MR = Membrane Reactor

n = Order of Reaction

N_A = no. of moles A left un reacted

N_{A0} = Initial no. moles A

P = Pressure atm .

R = The Universal Gas Constant 0.082 lit . atm .

RWGS = Reverse Water Gas Shift Reaction .

SEM = Scanning Electron Microscope .

SMSI = Strong Metal Support Interaction

T = Temperature °C

TG = Thermal Gravimetric Analysis .

TOF = Turn Over Frequency

TPR = Temperature Programmed Reduction

TR = Tubular Reactor

V₀ = Initial Volume of Reactants

W = Weight of Catalyst gm .

WGSR = Water Gas Shift Reaction

WHSV = Weight Hourly Space Velocity ccg⁻¹h⁻¹

X_A = Conversion

XANES = X – Ray Absorption Near – Edge Structure

τ' = Weight – Time Term kg.h lit⁻¹

ε_A = change in the system volume between no conversion and complete conversion .

AIM OF THE WORK

Aim of the work

This work aims to study the reforming of Egyptian natural gas rather than pure methane (as usually reported in literature) by carbon dioxide .

Three proposed noble metals namely Rh , Ru and Ir supported on γ - alumina in the ratio 0.5 % by wt are used as catalysts .

The effect of reaction conditions ; temperatures , space velocities are studied at different levels in order to optimize the reaction parameters .

Finally the reaction kinetics for the reforming of CO₂ and methane using the different catalysts are studied .

ABSTRACT

ABSTRACT

Elsalamony, Radwa Abbas. On Reforming of Natural Gas by Carbon dioxide to Produce Synthesis Gas. MSc, Egyptian Petroleum Research Institute , 2005.

Reforming of natural gas with carbon dioxide to synthesis gas ($H_2 + CO$) has been investigated over rhodium , ruthenium and iridium (0.5 wt %) supported on γ – alumina catalyst . The catalysts were prepared from the corresponding metal salts by the impregnation technique . 2 gm of each catalyst were tested in a tubular flow reactor 13 mm diameter and 120 mm length . The catalyst's activity was investigated at three reaction temperatures namely 600 , 700 and 800°C , and different weight hourly space velocities 18000 , 36000 , 45000 and 60000 $cc.g^{-1}.h^{-1}$. Both major and minor components in the natural gas were determined using high sensitive gas chromatographic techniques .

All the catalysts showed reactivity towards the reforming reaction but with varying degrees.

Generally ; the activity of the reforming reaction towards all natural gas components increased with increasing temperature and decreasing space velocity i.e. increasing contact time . From the results obtained, the optimum reforming conditions for each catalyst w.r.t . natural gas components could be established .

In addition , the optimum conditions for obtaining the maximum H_2 / CO ratio were also evaluated for the investigated catalysts .

The maximum ratio for Rh / γ - Al_2O_3 catalyst was at 700°C and 36000 $cc g^{-1} h^{-1}$, for Ru / γ - Al_2O_3 catalyst was at 800°C and 18000 $cc g^{-1} h^{-1}$ and for Ir / γ - Al_2O_3 catalyst was at 700°C and 36000 $cc g^{-1} h^{-1}$.

All three catalyst obeyed the 1st order reaction rate assumption w.r.t. both reactants CO_2 and CH_4 under all reaction temperatures . The dependence of the

reaction rate constant on temperature was determined by the Arrhenius' plot .
The average activation energy for CO₂ was 46.25E3 J / mol. and that of CH₄
was 31.52E3 J / mol ,

Key words :-

natural gas , CO₂ , Rh , Ru , Ir , γ - Al₂O₃ , CO₂ reforming of CH₄ , heavy
components , chromatograph , space velocity , temperature , kinetics .